

TAH PLASTIC HiCo 2750e

plastic cards and bank cards

TRANSFER FOIL, HIGH COERCIVITY, (PROTECTIVE LAYER)

TAH magnetic foil uses state of the art Barium ferrite oxide to achieve high signal levels, conforming to ISO7811/6. TAH is a transfer foil with a protective layer on the magnetic coating to provide enhanced durability, mark resistance and slip. Applications include normal transfer onto PVC overlay for sandwich thermo lamination and in line transfer on to core PVC sheets.

Characteristics	TAH F27	TAH F28D	TAH F24	TAH F41D
BASE FILM	Polyester	Polyester	Polyester	Polyester
BASE THICKNESS	15µm	15µm	15µm	15µm
TOTAL THICKNESS	26 ± 1µm	27 ± 1µm	26 ± 1µm	25 ± 1µm
OXIDE COLOUR	Purple/Black	Black	Black	Black
WINDOW OUTPUT	100 ±5%	100 ±5%	100 ±5%	100 ±5%
ACTIVATION TEMP	140-150°C	140-150°C	110-120°C	140-150°C
SPECIAL FEATURES	Purple Oxide Colour	PC, Special PET	PLA Eco Cards	Press Polish lamination

AVERAGE READ BACK SIGNAL	80% < = Average Read Back Signal < = 120%
AVERAGE WRITE CURRENT	350% < = Average Write Current < = 500%
ABRASION RESISTANCE	>70% of initial reading, 250 Taber cycles / 4000 ISO head cycles
RETENTIVITY	106 +/- 10% mT
SQUARENESS Br/Bs	>0.80
REMANENCE	1.22 mx/cm +/- 10.0%

Best used within two years of the date received.

TAH Plastic 2750 tech-2 September 25